

SUPPLEMENTAL SPECIFICATION**AMENDMENT TO SECTION 593 – GEOTEXTILE**

The purpose of this supplemental specification is to present the NTPEP audit program for geotextiles

Amend 593.2.1 to read:

2.1 General. Geotextile shall be a product tested under the AASHTO National Transportation Product Evaluation Program (NTPEP) and included on the Qualified Products List for the Application, Strength Class, and Structure specified. Manufactures of geotextiles and those marketing geotextiles made by others as a “Private Labeler” shall participate in and maintain compliance with the NTPEP audit program for geotextiles. Manufacturer’s labels providing product name, AASHTO M288 class, roll number, and production date shall be affixed to both ends of the roll.

Replace 2.3.2 with:

2.3.2 Class 0. Geotextile specified as Class 0 (extra high strength) shall meet the following minimum requirements:

Geotextile Property	Test Method	Property Requirement [lb. (N)]
Grab Tensile Strength	ASTM D 4632	375 (1670)
Sewn Seam Strength	ASTM D 4632	335 (1500)
Tear Strength	ASTM D 4533	135 (600)
Puncture Strength	ASTM D 6241	1237 (5500)